


兆晶科技擁有完整的藍寶石晶圓加工生產線，並以專業且豐富的工程經驗、完整且嚴格的品質管制、熱忱的服務態度、良好的客戶口碑，做為產品的品質保證。歡迎您隨時來電，讓我們竭誠為您服務，並期望您能成為我們不斷改善的動力，讓兆晶科技成為您不可或缺的事業夥伴！

Tera Xtal Technology has full sapphire wafer production lines, professional and abundant engineering experience, total and strict quality control, sincere service attitude and good reputation regarding the quality assurance of products. You are welcome to contact us for any service. Servicing you is the incentive for our continual improvement. Let us be your steadfast partner in your business development!



| Item (tolerance / unit) | Specification | | | | |
|-------------------------------------|---|---------------|-----------|-----------------|----------------|
| Diameter (± 0.20 mm) | 2" | 2.5" | 3" | 4" | 6" |
| | 50.8 | 62.0 or 61.75 | 76.2 | 100.0 | 150.0 |
| Thickness ($\pm 20\mu\text{m}$) | 330 / 430 | 430 / 525 | 550 / 650 | 650 / 850 / 900 | 600 or others |
| Orientation (± 0.1 degree) | C-axis [0001], A-axis[11-20], M-axis[1010], R-axis[1-102] or others tilted with off angle of 0 / 0.2 / 0.35 / 1.0 degree or specified | | | | |
| Primary Flat (± 1.0 mm) | 16.0 | 16.0 | 22.0 | 32.0 | customized |
| PF Location (± 0.5 degree) | A-axis [11-20] (C-axis of Orientation) | | | | customized |
| Front-side Surface (nm) | Ra < 0.3 | | | | Ra < 0.2 |
| Back-side Surface (μm) | Fine Ground, Ra = 0.5 ~ 1.2, by customized | | | | Ra = 0.4 ~ 0.8 |
| TTV (μm) | < 10 | < 10 | < 10 | < 15 | < 25 |
| Bow (μm) | < 10 | < 15 | < 20 | < 25 | < 30 |
| Package | Clean Room, Nitrogen Atmosphere | | | | |
| Application | LED epitaxy, SOS substrates or others. | | | | |

*All specifications shown above are of typical requirements. They can be customized per customer's request.

| 總公司 TERA XTAL TECHNOLOGY CORPORATION | 統一編號：70778284
 | 地址：300 新竹市科學工業園區園區二路9之1號
 NO.9-1, PARK AVENUE 2, HSINCHU SCIENCE PARK, HSINCHU 300, TAIWAN, R.O.C.
 | TEL : +886-3-666-8779 | FAX : +886-3-666-8559

| 楊梅分公司 YANGMEI PLANY | 統一編號：28112759
 | 地址：326 桃園縣楊梅鎮秀才路968號
 NO.968, SHIOUTSAI ROAD, YANGMEI JEN, TAOYUAN, 326 TAIWAN, R.O.C.
 | TEL : +886-3-288-8989 | FAX : +886-3-288-8862



兆晶科技股份有限公司
TERA XTAL TECHNOLOGY CORPORATION

| 日本販売代理店 (株)ニューメタルス エンド ケミカルス コーポレーション
 | 電子材料部/水戸 E-mail: mmito@newmetals.co.jp Tel:06-6202-5108 Fax:06-6223-0987