



▶ PRODUCT BENEFITS

Optimized fuel cell performance by application

Gas permeability

Conductivity

Physical property uniformity

Cost effective, high volume manufacturing methods

PRODUCT AVAILABILITY

Rolls:

400 mm or 800 mm width 10 - 800 m length Cores 6" / 152 mm ID

Cut sheets, samples available upon request

► AvCarb® Gas Diffusion Systems for Fuel Cells

AvCarb Material Solution's series of AvCarb Gas Diffusion Systems combine BMP's proprietary carbon fiber paper, a PTFE treatment, and micro-porous layer coating, each designed for the rigorous demands of specific fuel cell applications such as PEMFC, DMFC, and PAFC.

AvCarb Gas Diffusion Systems are based upon carbon fiber paper. AvCarb carbon fabrics and AvCarb Molded Graphite Laminates treated with PTFE and micro-porous layers for fuel cell applications are also available.

Please consult our GDL product selection guide for help in identifying the optimal GDL design for your application.



AvCarb Gas Diffusion Systems are fuel cell gas diffusion layers combining a carbon fiber paper substrate, a PTFE coating, and a surface microporous layer of PTFE and carbon particles. The table below lists nominal properties of commercially available AvCarb Gas Diffusion Systems, which have been engineered for optimal performance for selected fuel cell applications.

For assistance in selecting the right GDS product for your application, please refer to the AvCarb Gas Diffusion Layer Selection Guide, or contact us.

| TYPICAL PROPERTY | UNITS | AvCarb GDS3215 | AvCarb GDS3250 | Avcarb GDS3260 | Avcarb GDS2230 | Avcarb GDS2240 | Avcarb GDS22100 | Avcarb GDS2120 | Avcarb GDS1120 |
|---|----------|-------------------|-------------------|-------------------|-------------------|-------------------|--------------------|-------------------|-------------------|
| Base Material | | AvCarb EP40 | AvCarb EP40 | AvCarb EP40 | AvCarb P75 | AvCarb P75 | AvCarb P75 | AvCarb P75 | AvCarb P50 |
| Nominal Thickness | | | | | | | | | |
| (@ 5.00 N/cm2) | microns | 200 | 225 | 210 | 275 | 275 | 330 | 248 | 184 |
| Nominal Basis Weight | g/m2 | 60 | 75 | 80 | 98 | 110 | 185 | 101 | 79 |
| Break Strength | | | | | | | | | |
| machine direction | MPa | 12.0 | 12.0 | 14.0 | 6.5 | 8.5 | 8.0 | 25.0 | 18.0 |
| cross machine direction | MPa | 5.0 | 7.0 | 8.5 | 4.0 | 5.5 | 5.0 | 15.0 | 10.0 |
| Stiffness | | | | | | | | | |
| machine direction | Taber | 12.0 | 10.0 | 10.0 | 22.0 | 22.0 | | 21.0 | 10.0 |
| cross machine direction | Taber | 5.0 | 8.0 | 8.0 | 20.0 | 20.0 | 18.0 | 14.7 | 6.0 |
| Bulk Density (@ 0.69 N/cm2 / 1psi) | g/cm3 | 0.30 | 0.33 | 0.38 | 0.35 | 0.40 | 0.53 | 0.40 | 0.40 |
| Compressibility (22N - 113N)/22 x 100% | % | 10.0 | 16.0 | 15.0 | 17.0 | 15.0 | 7.0 | 11.0 | 14.0 |
| Through-Plane Resistivity | mOhm*cm2 | <14.0 | <14.0 | <14.0 | <14.0 | <14.0 | <17.0 | <14.0 | <14.5 |
| Typical Roll Width | mm | 400/800 | 400/800 | 400/800 | 400/800 | 400/800 | 400/800 | 400/800 | 400/800 |